

ISOMAT PU-FOAM

Polyurethane foam, hand-held

Description

ISOMAT PU-FOAM is a moisture-curing, self-expanding, one-component polyurethane foam that comes with a plastic nozzle for easy application. It provides excellent adhesion to most common building materials, including wood, plaster, concrete, stone, metal, etc. while offering thermal and sound insulation properties along with resistance to moisture and aging.

Fields of application

ISOMAT PU-FOAM is suitable for mounting and sealing gaps around door and window frames, for filling holes, voids and cavities, for filling around pipe penetrations in walls, etc.

Technical data

Base:	polyurethane
Color:	yellow
Density:	16-20 kg/m ³
Tack-free time: (TM 1014-2013)	8 min (+20°C, R.H. 60%)
Cutting time (2 cm diameter strip): (TM 1005-2013)	max. 30 min (+20°C, R.H. 60%)
Final curing time:	12 h (+20°C, R.H. 60%)
Dimensional stability: (TM 1004-2013)	max. ± 5% (+20°C, R.H. 60%)
Reaction to fire: (DIN 4102)	B3
Foam yield: (TM 1007-2013)	25-30 l
Application temperature:	from +5°C to +35°C

Directions for use

1. Substrate preparation

The substrate must be clean, free of dust, loose particles, grease, oil etc. and dampened prior to application.

2. Application

The can should be shaken vigorously for at least 1 min before use. Then the lid must be removed and the plastic nozzle fixed onto the can. The can should be held upside down, making sure the valve is facing downwards while dispensing. The foam flow can be regulated by applying different pressure on the valve. Care must be taken not to overfill the joints as the foam expands during curing. Joints up to 5 cm wide should be filled in multiple layers with a maximum width of 2 cm each. Fresh foam should be sprayed with water after application to stop post-expansion.

In the event of long interruptions of use, the can should be shaken again.

Consumption

One can yields up to 25-30 l of cured foam, but the exact volume depends on application conditions (temperature, humidity, space available for expansion, etc.).

Packaging

750 ml cans.

Shelf life – Storage

18 months from production date, stored in an upright position with the valve facing upwards, in dry and well-ventilated areas, at temperatures between +5°C to +25°C.

ISOMAT PU-FOAM

Remarks

- The optimal can temperature for application is +15°C to +25°C.
- Cured foam must be protected from prolonged UV light exposure.
- Fresh foam can be removed with ISOMAT PU-FOAM CLEANER, while cured and hardened foam can be removed only mechanically.
- Volume and quality of cured foam is affected by relative air humidity. Intensive moistening is necessary when relative humidity is below 35%.
- ISOMAT PU-FOAM does not adhere to polyethylene (PE), polypropylene (PP), Teflon (PTFE) and silicone.
- Protective glasses and gloves should be used during application. For more information, please refer to the relevant Safety Data Sheet (MSDS).
- Consult the directions for safe use and precautions written on the package before use.

ISOMAT S.A.
BUILDING CHEMICALS, MORTARS & PAINTS
HEADQUARTERS – THESSALONIKI, GREECE
17th km Thessaloniki – Ag. Athanasios Road
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece
T +30 2310 576000
www.isomat.eu e-mail: support@isomat.eu